



# Grip ALL Solvent Based

## Product description

Grip ALL Solvent Based is a fibre reinforced, ready to use, solvented construction adhesive based on synthetic rubber. Compatible with most building materials (porous and non-porous).

## Properties

- Fibre reinforced
- Direct application onto one substrate
- Fast build-up of end strength
- Makes the use of screws and nails redundant
- Suitable for uneven surfaces
- Suitable for interior and exterior applications

## Applications

- Suitable for bonding panel work, panels, skirting boards of wood and PVC, cable tray and the most frequent decoration materials
- Bonding of carpet grippers, edge strips and stair nosing
- Suitable for solid fixing of materials like wood, synthetic materials, stone, wall tiles, metal on surfaces of concrete, stone, plasterwork, wood, chipboard etc.
- Bonding of wall and floor boards, window frames and partitions



## Technical data

Base	SBR rubber
Consistency	Paste
Curing system	Physical drying and crystallisation
Density	ca. 1,35 g/ml
Open time	ca. 5 minutes
Application temperature	5°C - 30°C
Temperature resistance	-20°C → +70°C

*Footnote: evaporation time, open time and curing speed may vary depending on environmental factors such as temperature, moisture, and type of substrates.*

## Substrates

- Substrate condition  
Clean, free of dust and grease.
- Substrate preparation  
No pretreatment required.
- Substrate types  
Grip ALL Solvent Based has a good adhesion to following substrates: all common materials. Grip ALL Solvent Based has no good adhesion or is not suitable for PE, PP, PTFE (Teflon®), bituminous substrates. We recommend a preliminary adhesion and compatibility test on every surface.



# Grip ALL Solvent Based

## Application method

### ■ Application method

Apply the adhesive by means of a caulking gun in equal beads or dots, not too thin, every 15 cm and on one of the materials that have to be bonded. Always apply adhesive to the edges and corners Press both parts together, immediately pull loose and let dry for 10-15 minutes. Afterwards bond again and batten with a rubber hammer. If necessary, support the bonded materials. Apply the transfer method to bond any wallcovering panels and other heavy materials, ie. pressing the parts first against each other, separate immediately and after 5 min bond parts together and batten. The bond can be fully loaded after 24-48 hours.

## Health- and Safety Recommendations

Dangerous. Respect the precautions for use.

Use only in well-ventilated areas.

In case of insufficient ventilation it is appropriate to wear respiratory protection.

Take the usual labour hygiene into account. Consult the packaging label and safety data sheet for more information.

## Packaging/Logistics

Packaging: Various sizes available. Please consult the product catalogue, the Soudal website or a Soudal representative.

Shelf life: 12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C

## Remarks

- The applied pressure and not the duration of the pressure will determine the ultimate strength of the bond.
- Do not use as a mirror adhesive.
- Do not use in applications where continuous water immersion is possible.
- In case of overhead applications a combination with mechanical fixing is required.

This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. It is general in nature and does not constitute any liability. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application. In every case it is recommended to carry out preliminary experiments. The manufacturer reserves the right to modify products without prior notice.