



## Injection Cream 80 [basic]

Silane cream for use as a horizontal barrier against rising damp in masonry



Availability		
Quantity per pallet	64	32
<b>Size / Quantity</b>	<b>5 l</b>	<b>12,5 l</b>
Type of container	Plastic bucket	Plastic bucket
Container code	05	13
<b>Art. no.</b>		
0691	■	■

### Application rate

For details see the application rate table under Application examples

Application rates will be higher for hollow masonry.



### Range of use

- Porous, mineral building materials such as clay brick, sandstone and sand-lime brick
- Subsequent cross-sectional waterproofing of masonry under gravity up to moisture penetration of 95%



### Property profile

- New inverse formulation for faster action
- Silane/siloxane-based
- Optimised for injection under gravity
- High yielding
- Water repellent



### Characteristic data of the product

Density (20 °C)	Approx. 0.94 g/cm <sup>3</sup>
Flash point °C	> 100 °C
Appearance/colour	Milky, white
Consistency	Cream

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

### Possible system products

- [WP Sulfatex \(0430\)](#)
- [WP Sulfatex rapid \(0429\)](#)
- [WP DS Level \(0426\)](#)

### Preparation


- **Substrate requirements**  
Drilling channel must be free of drill dust.
- **Substrate preparation**  
Creating boreholes: Single row, diameter 12 mm, spacing 12 cm, horizontal plane, borehole depth up to approx. 5 cm from end of wall.  
For walls > 0.6 m thick, it is recommended to make the series of drill holes on both sides.

### Directions

#### ■ Conditions for use

Temperature of the material, air and substrate: from min. +5 °C to max. +30 °C.

Inject material using suitable injection apparatus depending on the packaging type.  
Do not fill the front 2 cm of the drill holes with cream.





**Tips on use**

Take appropriate measures to protect adjacent building elements and materials that should not come into contact with the product.  
Close drill holes on the same day using WP DS Level (Art. 0426).  
Temporary discolouration of the surface may occur in the areas in which the material propagates, in particular on fair-faced masonry.  
For the subsequent surface sealing, it is recommended to apply an additional coat of WP DS Level (Art. 0426) in the region of the row of drill holes.  
Then, apply surface waterproofing to at least 30 cm above and below the row of drill holes. Include adjacent components if necessary.  
We recommend setting up trial areas.

**Application examples**

■ **Application rate table**

Application rate equals the drill hole volume for filling plus a safety margin.  
Drill hole diameter: 12 mm  
Drill hole spacing: 12 cm, i.e. 8.3 holes per m

Wall thickness:	Drill hole depth:	Application rate* per m:
10 cm	approx. 8 cm	<b>approx. 80 ml</b>
11.5 cm	approx. 9.5 cm	<b>approx. 100 ml</b>
24 cm	approx. 22 cm	<b>approx. 230 ml</b>
36 cm	approx. 34 cm	<b>approx. 350 ml</b>
42 cm	approx. 40 cm	<b>approx. 415 ml</b>

\* approx. 10% safety margin included

**Notes**

Not suitable for aerated concrete, gypsum and clay building materials.  
Not suitable for new grouting mortar.  
A test of effectiveness needs to be carried out on carbonaceous natural stone.  
The relevant test certificates must be observed when planning and carrying out work.  
The applicable regulations and legal requirements must be observed.  
Information on planning injection processes with and processing certified injection materials against capillary moisture transport can be found in WTA Code of Practice 4-10 and must be taken into account.

**Tools / Cleaning**




Sealant gun,  
Injection lance for 550 ml,  
Injection hose for 550 ml,  
Injection kit for 550 ml,  
Desoi PowerPump 70 for 10 l politainer,  
Low-pressure, conveying and spraying equipment with a suitable injection lance

Clean tools and remove spilled material while it is still wet using Aqua RK-898 Cleaning Concentrate (3868) or Thinner V 101 (0978).  
If the machine is to be left unused for longer periods, drain it and clean with RK-898 or Thinner V101.  
Ensure that any residue from cleaning is disposed of correctly.  
Please contact Remmers Technical Service (phone +49 5432 83900) before applying with machine processing.

**Remmers tools**

➤ **Injektionsset (4195)**

**Storage / Shelf life**



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 12 months.

**Safety data / Regulations**

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

**Personal protective equipment**

Wear suitable gloves, eye protection and protective clothing.

**Disposal**

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.



Biocidal Products Regulation

Contains a biocidal product (in-can preservative) with the biocidal agents CMIT/MIT (3:1) for protecting the container content from deterioration by microbial organisms (germs, yeast, etc.). Please note the processing guidelines carefully!

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.