



Kiesol

Single-component, solvent-free, strengthening silicification concentrate



Availability							
Quantity per pallet	360	84	50	24	2	1	
Size / Quantity	1 kg	5 kg	10 kg	30 kg	210 kg	1000 kg	
Type of container	Tin canister	Tin canister	Tin canister	Tin canister	Drum	Container	
Container code	01	05	10	30	69	61	
Art. no.	1810	■	■	■	■	■	■

Application rate



Subsequent horizontal waterproofing:
 Approx. 1.5 kg/m per 10 cm wall thickness (can vary significantly depending on porosity of masonry)
 Priming:
 Approx. 0.1 - 0.3 kg/m² (dilute 1:1 with water)
 Surface improvement:
 Approx. 0.2 - 0.4 kg/m²

Range of use



- Porous, mineral building materials such as fired and sand-lime brick, sandstone, mineral renders
- Subsequent horizontal waterproofing of masonry under gravity up to a degree of moisture penetration of 80%
- Subsequent horizontal waterproofing of masonry under low pressure up to a degree of moisture penetration of 95%
- Priming for protection against rear moisture penetration
- Surface improvement

Property profile



- Strengthens
- Narrows pores
- Repels water
- Inhibits masonry salt
- Improves adhesion, abrasion resistance and surface strength
- Increases resistance to chemical attack

Characteristic data of the product

Density (20 °C)	Approx. 1.15 g/cm ³
Strengthening	≤ 5 N/mm ²
Water repellency	w < 0.5 kg/(m ² *h ^{0.5})
Water vapour permeability	> 90%
Appearance/colour	Clear to yellowish
pH value	Approx. 11

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Certificates

- [WTA certificate](#)

Additional information

- [Historical test certificates](#)
- [1st BAM - Test certificate borehole method](#)
- [2. Report "Institut für Bauphysik" No. 9724-HG-P-93, long-term effect: Alte Oper Frankfurt](#)
- [3rd BAM - Testing the effectiveness of subsequent wall drying](#)
- [4. "Hygiene-Institut Gelsenkirche" - drinking water matters](#)
- [5. "Hygiene-Institut Gelsenkirchen" - Test certificate in accordance with DVGW worksheet W 347](#)
- [6. Test certificate toxicological evaluation](#)

Possible system products

- [Remmers interior and exterior waterproofing systems](#)
- [BIT 1K \(basic\) \(0872\)](#)



- › BIT 2K ^[basic] (0871)
- › WP Sulfatex (0430)
- › WP DS Levell (0426)
- › WP Sulfatex rapid (0429)
- › WP DKS rapid ^[basic] (0423)
- › WP Top ^[basic] (0428)
- › BSP 6 (0309)

Preparation

■ Substrate requirements

Subsequent horizontal waterproofing of masonry

Drilling channel must be free of drill dust.

Priming for protection against the effect of water from behind

The substrate must be clean and free of oil, grease and release agents.

Surface improvement

The substrate must be clean and free of oil, grease and release agents.

■ Substrate preparation

Subsequent horizontal waterproofing of masonry

Dam the injection area at least 30 cm above and below the row of boreholes (Kiesol MR 1:1 and rigid waterproofing slurry).

Production of boreholes:

Diameter 12 - 30 mm, spacing 10 - 12.5 cm, angle of inclination approx. 45°, borehole depth up to approx. 5 cm from end of wall.


For walls > 0.6 m thick, it is recommended to make the series of drill holes on both sides.

Pre-inject BSP 3 or BSP 6 (borehole suspension) into hollow masonry.

Re-pierce filled boreholes after incipient hardening of the BSP.

Wait 7 days before carrying out further work.

Directions



■ Conditions for use

Temperature of the material, air and substrate: from min. +5 °C to max. +35 °C.

Subsequent horizontal waterproofing of masonry

- Under gravity (moisture penetration < 80%):

Using a suitable vessel, e.g. Kiesol Metering Cartridge (417301), fill (multiple times if necessary) until saturated.

- Low pressure (moisture penetration < 95%):

Inject using suitable injection equipment and injection packers.

Priming for protection against the effect of water from behind

Apply material in sections until saturated.

If necessary: pre-wet highly absorbent substrates with water.

Surface improvement

Apply material in sections.

Repeat the procedure (wet-on-wet) until no more material uptake is observed.

Tips on use

Take appropriate measures to protect adjacent building elements and materials that should not come into contact with the product.

Subsequent horizontal waterproofing of masonry

After injection, fill the boreholes with borehole suspension.

Not suitable for injections in porous concrete, gypsum and clay building materials.

Priming for protection against the effect of water from behind

Immediately remove excess product.

Do not allow the primer to dry out.

Perform subsequent operations wet-on-wet, within the reaction time.

Surface improvement

Protect freshly treated surfaces from driving rain, wind, sunlight and condensation.

Not suitable for improving surfaces where higher requirements are placed on appearance.

We recommend setting up trial areas.

Notes

The relevant test certificates must be observed when planning and carrying out work.

The applicable regulations and legal requirements must be observed.

Information on planning injection processes with and processing certified injection materials against capillary moisture transport can be found in WTA Code of Practice 4-10 and must be taken into account.



Tools / Cleaning




Brush, surface sprayer, airless spraying equipment, pouring vessel, low-pressure injection apparatus
Additional equipment according to tool programme

Clean tools immediately after use with water.
Ensure that any residue from cleaning is disposed of correctly.

Remmers tools

- > **Druckschlauch mit Greifkopf (4371)**
- > **Lamellenschlagpacker (4524)**
- > **Setzwerkzeug (4523)**
- > **Kiesol Dosierkartusche (4173)**
- > **Greifkopf (4037)**
- > **Gloria Drucksprüher Pro 100 (4668)**
- > **Flächenstreicher (4540)**
- > **Heizkörperpinsel (4541)**

Storage / Shelf life



At least 36 months in unopened, original containers stored cool, dry and protected from frost.

Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Personal protective equipment

Respiratory protection with a particle filter P2 must be worn during spraying, together with protective goggles. Wear suitable protective gloves and clothing.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.